

ATTACHMENT B

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application.

1. (Original) A supported metallic compound comprising a support based on aluminium oxide onto which a tungsten hydride is grafted.
2. (Currently Amended) A compound according to claim 1, ~~characterised~~characterized in that the support is selected from among supports with a homogenous composition based on aluminium oxide and from among heterogeneous supports based on aluminium oxide comprising aluminium oxide essentially at the surface of said supports.
3. (Currently Amended) A compound according to claim 1 ~~or claim 2~~, ~~characterised~~characterized in that the support has a specific surface area (BET) selected in a range of from 0.1 to 1000 m²/g, preferably from 0.5 to 800 m²/g.
4. (Currently Amended) A compound according to ~~any one of claims 1 to 3~~ claim 1, ~~characterised~~characterized in that the support comprises aluminium oxide, mixed aluminium oxides or modified aluminium oxides, in particular modified by one or more elements from groups 15 to 17 of the periodic table of the elements.
5. (Currently Amended) A compound according to claim 4, ~~characterised~~characterized in that the support comprises aluminium oxide selected from among porous aluminas, non-porous aluminas and mesoporous aluminas.
6. (Currently Amended) A compound according to claim 5, ~~characterised~~characterized in that the porous alumina is selected from among γ -alumina, η -alumina, δ -alumina, θ -alumina, κ -alumina, ρ -alumina and χ -alumina, preferably from among γ -alumina and η -alumina.

7. (Currently Amended) A compound according to claim 6, ~~characterised~~characterized in that the porous alumina has a specific surface area (BET) in a range of from 100 to 1000 m²/g, preferably from 300 to 1000 m²/g, in particular from 300 to 800 m²/g.

8. (Currently Amended) A compound according to claim 5, ~~characterised~~characterized in that the non-porous alumina is α -alumina.

9. (Currently Amended) A compound according to claim 8, ~~characterised~~characterized in that the non-porous alumina has a specific surface area (BET) in a range of from 0.1 to 300 m²/g, preferably from 0.5 to 300 m²/g, in particular from 0.5 to 250 m²/g.

10. (Currently Amended) A compound according to claim 6 ~~or claim 7~~, ~~characterised~~characterized in that the porous alumina comprises a mixture of one or more crystalline forms of porous aluminas with α -alumina, in particular in a proportion by weight of from 20 to 80%.

11. (Currently Amended) A compound according to claim 4, ~~characterised~~characterized in that the mixed aluminium oxides are selected from among aluminium oxides combined with at least one other oxide in a proportion by weight of preferably from 2 to less than 80%, in particular from 2 to less than 50%, in particular from 2 to less than 40%.

12. (Currently Amended) A compound according to claim 11, ~~characterised~~characterized in that the other oxide(s) are oxides of the elements, M, selected from among the metals of groups 1 to 13 and the elements of group 14, with the exception of carbon, of the periodic table of the elements.

13. (Currently Amended) A compound according to claim 11, ~~characterised~~characterized in that the other oxide(s) are selected from among oxides of alkali metals, of alkaline-earth metals, of transition metals and of the elements of groups 13 and 14, with the exception of carbon, of the periodic table of the elements.

14. (Currently Amended) A compound according to claim 4, ~~characterised~~characterized in that the modified aluminium oxides comprise one or more of the elements of groups 16 or 17 of the periodic table of the elements, and are preferably selected from among superacids of alumina and sulfated, sulfided, fluorinated and chlorinated aluminium oxides.

15. (Currently Amended) A compound according to ~~any one of claims 1 to 14~~ claim 1, ~~characterised~~characterized in that it assumes the form of particles having an average size of from 10 nm to 5 mm, preferably from 20 nm to 4 mm.

16. (Currently Amended) A compound according to ~~any one of claims 1 to 15~~ claim 1, ~~characterised~~characterized in that the oxidation state of the tungsten has a value selected in a range of from 2 to 6, preferably from 4 to 6.

17. (Currently Amended) A compound according to ~~any one of claims 1 to 16~~ claim 1, ~~characterised~~characterized in that the tungsten atom is attached to one or more hydrogen atoms and optionally to one or more hydrocarbon residues, R.

18. (Currently Amended) A compound according to claim 17, ~~characterised~~characterized in that the hydrocarbon residues R are identical or different, saturated or unsaturated hydrocarbon residues, comprising in particular from 1 to 20, in particular from 1 to 10 carbon atoms and optionally comprising silicon.

19. (Currently Amended) A compound according to ~~any one of claims 1 to 18~~ claim 1, ~~characterised~~characterized in that the tungsten atom is complexed by one or more hydrocarbon ligands, in particular aromatic ligands or carbonyl ligands.

20. (Currently Amended) A compound according to ~~any one of claims 1 to 19~~ claim 1, ~~characterised~~characterized in that, under infrared spectroscopy, it exhibits at least one of the two absorption bands at 1903 and 1804 cm^{-1} .

21. (Currently Amended) A compound according to ~~any one of claims 1 to 20~~ claim 1, ~~characterised~~characterized in that, when examined by proton nuclear magnetic resonance (solid $^1\text{H-NMR}$) at 500 MHz, it exhibits a tungsten hydride chemical shift value ($\delta_{\text{W-H}}$) equal to 10.6 ppm.

22. (Currently Amended) A method for production of the compound according to ~~any one of claims 1 to 21~~ claim 1, ~~characterised~~characterized in that it comprises (1) a dispersion and grafting step of an organometallic tungsten precursor, Pr, onto a support based on aluminium oxide, in which precursor the tungsten is in particular attached or complexed to at least one hydrocarbon ligand, so as to form a hydrocarbon compound or complex of tungsten grafted onto said support, then (2) a hydrogenolysis step of the grafted hydrocarbon compound or complex of tungsten, arising from the preceding step, so as to form a tungsten hydride grafted onto said support.

23. (Currently Amended) A method according to claim 22, ~~characterised~~characterized in that the support based on aluminium oxide is subjected to a prior calcination and/or dehydroxylation step.

24. (Currently Amended) A method according to claim 22 ~~or claim 23~~, ~~characterised~~characterized in that the dispersion and grafting step is performed by sublimation, by impregnation with the assistance of a solvent, or by dry mixing.

25. (Currently Amended) A method according to ~~any one of claims 22 to 24~~ claim 22, ~~characterised~~characterized in that the hydrogenolysis step is performed by contacting the grafted hydrocarbon compound or complex of tungsten with hydrogen or a reducing agent.

26. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~ in a method making use of hydrocarbon cleavage and recombination reactions.

27. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~
claim 1 as a hydrocarbon, in particular alkane, metathesis reaction catalyst.

28. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~
claim 1 in a method for manufacturing hydrocarbon(s) having a modified carbon
skeleton by the reaction of at least one aliphatic hydrocarbon with itself, or with at least
one other aliphatic hydrocarbon, or with at least one aromatic or cyclanic hydrocarbon
substituted by at least one alkyl residue.

29. (Currently Amended) Use according to claim 28, ~~characterised~~characterized in that
the aliphatic hydrocarbon is selected from among linear aliphatic hydrocarbons, in
particular from C₂ to C₃₀, and branched aliphatic hydrocarbons, in particular from C₄ to
C₃₀, the aromatic hydrocarbon substituted by at least one alkyl residue is selected from
among substituted aromatic hydrocarbons from C₇ to C₃₀ with at least one linear or
branched alkyl residue, in particular from C₁ to C₂₄, and the cyclanic hydrocarbon
substituted by at least one alkyl residue is selected from among substituted cyclanic
hydrocarbons from C₄ to C₃₀ with at least one linear or branched alkyl residue, in
particular from C₁ to C₂₇.

30. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~
claim 1 in a method for manufacturing hydrocarbon(s) by reaction of methane with at
least one other aliphatic hydrocarbon, or with at least one aromatic or cyclanic
hydrocarbon substituted by at least one alkyl residue.

31. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~
claim 1 in a method for manufacturing alkane(s), in particular ethane, by reaction of
methane with itself.

32. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 21~~
claim 1 in a method for manufacturing hydrocarbon(s) by a crossed metathesis reaction
between at least one starting hydrocarbon and said compound.

33. (Currently Amended) Use of the compound according to ~~any one of claims 1 to 24~~ claim 1 in a method for manufacturing hydrocarbon(s) or hydrocarbon oligomer(s) or polymer(s) with a modified carbon skeleton by reaction of a starting hydrocarbon polymer with hydrogen.